


CLEAN COPY OF PENDING CLAIMS

1. (Amended) A process for producing a non-aqueous sol-gel spin-on glass material comprising a hybrid glass/polymer material, by reacting an alkyl substituted trialkoxysilane or dialkyl substituted dialkoxysilane with a silane diol, wherein said alkyl group has from 1 to 8 carbon atoms, wherein the reaction of the alkyl substituted trialkoxysilane or dialkyl substituted dialkoxysilane silane with the silane diol is carried out in a non-aqueous medium in the presence of a catalyst, wherein the catalyst is selected from: a) a tin catalyst or b) a dibutyltin diluarate, titanium isopropoxide, acetic acid or trifluoroacetic acid catalyst.
2. (Original) The process of claim 1, wherein the silane diol is a diphenylsilanediol, a 1,3-Bis (3-hydroxypropyl) tetramethoxysilane, a 1,3-Bis (4-hydroxybutyl) tetramethylsilane, a fluorinated silane diol, or a mixture of one or more of these silane diols.
3. (Original) The process of claim 1, wherein the alkyl group is replaced with a methacryloxypropyl, acryloxypropyl, or epoxy moiety.
5. (Original) The process of claim 1, wherein the trialkoxysilane or dialkoxysilane has 1 to 3 C₁ to C₈ alkyl, methacryloxypropyl and/or alkoxy groups on the same molecule.
7. (Original) The process of claim 1, further comprising adding a phosphor dopant.
8. (Amended) The process of claim 7, wherein the phosphor dopant comprises YAG base phosphor or moisture sensitive phosphor nano-particles or an organic material selected from organic dyes or metal complexes.
9. (Original) The process of claim 1, further comprising adding a UV light blocking material and/or an oxygen scavenger.

10. (Original) The process of claim 1, further comprising adding a light-scattering material.
11. (Original) The process of claim 1, further comprising adding a coupling agent.
12. (Original) The process of claim 11, wherein the coupling agent is a dibutoxyaluminoxyltriethoxysilane, a mixture of zirconium isopropoxide and methacrylic acid, or another transition metal propoxide.
18. (Amended) A non-aqueous sol-gel spin-on glass material comprising a hybrid glass/polymer material containing a dopant, which comprises YAG base phosphor or moisture sensitive phosphor nano-particles, or an organic material selected from organic dyes or metal complexes, said sol-gel spin-on-glass material selected from the group having the following formulas:

Formula I




Where R = Hydrogen, C₁-C₈ Alkyl, Halogenated C₁-C₈ Alkyl or Glycidyoxyalkyl

R₁ = Ethyl, Propyl, another C₁-C₈ Alkyl, Halogenated C₁-C₈ Alkyl, Phenyl or Halogenated Phenyl

R₂ = Methyl, Ethyl or another C₁-C₈ Alkyl


X, Y = Si, Ge, Ti or Sn

Z = Alkyl, Substituted Alkyl, Phenyl, Substituted Phenyl

Formula IIWhere R = Alkyl (C₁-C₈), Phenyl, Substituted Phenyl


X, Y = Si, Ti, Ge or Sn

Z = Alkyl, Substituted Alkyl, Phenyl, Substituted Phenyl

Formula IIIWhere R₁ = Phenyl, Ethyl, Propyl, TrifluoropropylR₂ = Methyl, Ethyl

X, Y = Si, Ge, Ti or Sn

Z = Alkyl, Substituted Alkyl, Phenyl, Substituted Phenyl

Formula IV

Where R = Alkyl (C₁-C₈), Phenyl, Substituted Phenyl


R₁ = Alkyl, Phenyl

R₂ = Alkyl, Phenyl

X, U, Y = Si, Ge, Ti or Sn


Z = Alkyl, Substituted Alkyl, Phenyl, Substituted Phenyl.

23. (Original) The non-aqueous sol-gel spin-on glass material of claim 18, having the following formula:

Formula I


24. (Original) The non-aqueous sol-gel spin-on glass material of claim 18, having the following formula:

Formula II




25. (Original) The non-aqueous sol-gel spin-on glass material of claim 18, having the following formula:

Formula III



26. (Original) The non-aqueous sol-gel spin-on glass material of claim 18, having the following formula:

Formula IV




27. (Amended) The non-aqueous sol-gel spin-on glass material of claim 18, further comprising a UV light blocking material and/or an oxygen scavenger.
27. (Amended) The non-aqueous sol-gel spin-on glass material of claim 18, further comprising a light-scattering material.
34. (New) The non-aqueous sol-gel spin-on glass material of claim 18, wherein the phosphor dopant comprises YAG base phosphor or moisture sensitive phosphor nanoparticles.
35. (New) A process for producing the non-aqueous sol-gel spin-on glass material of claim 18, the process comprising reacting an alkyl substituted trialkoxysilane or dialkyl substituted dialkoxysilane with a silane diol, wherein said alkyl group has from 1 to 8 carbon atoms, wherein the reaction of the alkyl substituted trialkoxysilane or dialkyl substituted dialkoxysilane silane with the silane diol is carried out in a non-

aqueous medium in the presence of a catalyst, the process further comprising adding to said sol-gel spin-on glass material a phosphor dopant, which comprises YAG base phosphor or moisture sensitive phosphor nano-particles or an organic material selected from organic dyes or metal complexes.

36. The process of claim 35, wherein the phosphor dopant comprises YAG base phosphor or moisture sensitive phosphor nano-particles.

Respectfully submitted,


Andrew F. Sayko Jr.


Reg. No. 22,827

Andrew F. Sayko Jr.
1014 Crooked Oaks Lane
Seabrook Island, SC 29455
Tel: 908-612-0519
Fax: 843-243-0446

CERTIFICATE OF TRANSMISSION (37 CFR 1.8a AND 1.10)

I hereby certify that this correspondence (26 pages) is, on the date shown below, being transmitted by facsimile to the United States Patent and Trademark Office at Fax number (571) 273-8300.

Andrew F. Sayko Jr.:



Date: 17 August 2006